

# LvtANTISLIPMax

High density polyethylene underlay with antislip layer designed for LVT floors with CLICK system, offering very good floor heating compatibility.



## Product compatibility

- ✓ Consumer SPC and rigid LVT floors.

## Product highlights

- ✓ Closed cells UHD polyethylene foam.
- ✓ Very good floor heating compatibility.
- ✓ Antislip surface for locking system protection.
- ✓ No wave effect.

Symbol	Category	Value/Unit	Test methods
T	Thickness	1,2 mm ±10%	EN823
L	Length	15 000 mm ±4%	EN822
W	Width	1 000 mm ±2%	EN822
AW	Area weight	0,21 kg/m <sup>2</sup> ±10%	EN ISO 23997:2012
QW	Density	130 kg/m <sup>3</sup> ±10%	EN ISO 23996:2012
RWS	Reflected walking sound	12% ±2	IHD-W431
IS	Impact sound reduction	18 dB ±2	EN ISO10140, ISO717-2
CS	Temporary loads resistance	200 kPa ±10	EN 826:2013+A: FU1:2019
CC	Static loads (furniture) resistance	>50 kPa	EN1606
DL	Dynamic loads (walking) resistance	>100 000 cycles	EN13793
PC	Local unevenness compensation	0,95 mm ±10%	EN-ISO868
TR	Thermal insulation	0,024 m <sup>2</sup> K/W ±0,003	EN12667:2002 at 24°C
SD	Protection against moisture	<75 m	EN12086
RLB	Protection against falling objects	800 mm ±50	EN13329, EN438
RTF	Reaction to fire	---	EN ISO11925-2,PN-EN13501-1

Logistic Parameter	Sales unit	Packaging	Palette
Form	Roll	---	Corrugated box
Quantity	1 Pc.	---	33 Rolls
Area	15m <sup>2</sup>	---	495m <sup>2</sup>
Weight	3,15kg ± 10%	---	103,95kg ± 10%



Innovation and quality made in Poland. Since 2007.

Member of



rev. 04/2022

ITB-KOT-2019/0252.

Brandverhalten: normalentflammbar (Klasse E/ef)  
nach DIN EN 13501-1 oder Baustoffklasse DIN 4102-B2)  
Emissionsgeprüftes Bauprodukt nach DIBt-Grundsätzen.



## General information

All data are based on our experience and careful investigations. The diversity of the materials used, as well as the different construction site and processing conditions, can not be examined or influenced by us in detail. The quality and function therefore depends on the expert site evaluation and product use. In case of doubt, carry out your own tests or seek advice on our application technology. When processing, please observe the rules of technology as well as the manufacturing specifications of the building materials involved and constantly changing state of technology.

## Storage

Approx. 1 year, protecting from direct sunlight or other weather influences.

## Application

Unroll underlay on the sealed vapor barrier, with individual panels adjacent to one another and seal the joints with aluminum sealing tape.

Product information is subject to change without notice. Please visit our webpage for updated product informations.

